



Ref. T4/4.01

MSC/Circ.1006  
18 June 2001

**GUIDELINES ON FIRE TEST PROCEDURES FOR ACCEPTANCE OF  
FIRE-RETARDANT MATERIALS FOR THE CONSTRUCTION  
OF LIFEBOATS**

1 The Maritime Safety Committee, at its seventy-fourth session (30 May to 8 June 2001), noted that paragraph 4.4.1.4 of the International Life-Saving Appliance (LSA) Code as well as regulation VII/17 of the Torremolinos Protocol of 1993 relating to the International Convention for the Safety of Fishing Vessels, 1977 (1993 Torremolinos Protocol) uses the term “fire-retardant” with regard to materials for the construction of the hull and rigid cover of lifeboats, but there is no definition of fire-retardant material either in the LSA Code or in the 1993 Torremolinos Protocol.

2 The Committee, recalling that resolution 7 of the International Conference on Safety of Fishing Vessels held in 1993 in Torremolinos invited the Committee to develop an appropriate definition of fire-retardant materials together with the corresponding criteria related to the said definition as well as fire test procedures aimed at assessing compliance with the criteria for such materials, approved Guidelines on fire test procedures for acceptance of fire-retardant materials for the construction of lifeboats, as set out in the annex.

3 Member Governments are invited to apply the annexed Guidelines when approving fire-retardant materials used for the construction of lifeboats.

\*\*\*



## ANNEX

### **FIRE TEST PROCEDURES FOR ACCEPTANCE OF FIRE-RETARDANT MATERIALS FOR THE CONSTRUCTION OF LIFEBOATS**

#### **Application**

1 This test procedure should be used for the acceptance of fire-retardant and flame-resistant materials used for the construction of lifeboats which are required to be fire-retardant by the International Life-Saving Appliances Code and the Torremolinos Protocol of 1993 relating to the International Convention for the Safety of Fishing Vessels, 1977.

#### **Fire test procedure**

##### 2 General

Ignitability for fire-retardant laminate systems for the construction of lifeboats should be determined by ISO 5660-1: "Fire tests - Reaction to fire - Part 1: Rate of heat release from building products (Cone calorimeter method)", as described in paragraph 3. This test should be conducted for each resin used. In addition, a fire-retardant resin passing the test in paragraph 3 should undergo the test contained in paragraph 4.

#### **Fire-retardant test**

##### 3 Test specimens

Three test specimen laminates should be prepared reinforced with glass fibre of any form with a thickness of 5 mm and a minimum resin content of 40% by weight. Alternatively, three specimens of the specific laminate system should be tested as built. When similar laminates of different thickness are used, the minimum thickness should be tested. For laminates with normal thickness of greater than 50 mm, including sandwich construction, the requisite specimens should be obtained by cutting away the unexposed face to reduce the thickness to 50 mm. All specimens should be square with sides measuring 100 mm.

##### 3.1 Conditioning of specimens

Before the test, the specimens should be conditioned in sunlight to 300 MJ/m<sup>2</sup> (below 385 nm) of natural UV radiation exposure of outdoor weathering or acceptable equivalent accelerated artificial weathering exposure to the satisfaction of the Administration. Both natural and artificial exposures should include elevated temperatures of at least 30°C for substantial periods of the exposure and 20 % wet time.

### 3.2 Test conditions

The test should be performed in the horizontal position using a specimen edge frame, and the irradiance to the specimen during the testing should be kept constant. The test specimens should be tested to an irradiance of 50 kW/m<sup>2</sup>.

### 3.3 Duration of tests

The test should terminate when ignition occurs in the test specimen or at 10 min.

### 3.4 Test results

The average ignition time should be calculated as the arithmetic mean of the ignition time of the three specimens.

### 3.5 Acceptance criteria

The average ignition time should be greater than 40 s.

## **Flame-resistant tests**

### 4.1 Test procedure

GRP laminates representing the lay-up of a prototype boat, which should be based upon the minimum hull and/or canopy thickness to be used for the boat under consideration, should be tested to determine their resistance to the effects of flame impingement and strength. The test specimen should be cut from a one metre square panel of the above minimum thickness, which has been allowed to cure for not less than 21 days and then stored for 30 days at ambient temperature as stated below. The test should be carried out using the following methods:

- .1 the heat source to conduct the fire test should be provided by a gas torch fitted with a Sievert burner type No. 2944 or equivalent, giving a maximum flame temperature of approximately 1,600°C and burning propane at the rate of 4,110 grams per hour with a pressure of 0.2 MPa. During this procedure the rate of burning should be carefully controlled, with the length of blue flame being approximately 200 mm to the point of the greatest heat; and
- .2 the centre of a 450 mm by 450 mm test sample, cut from the one metre square panel (which should not be cut from the edges) should be exposed in the vertical plane perpendicular to the gel-coat surface to the tip of the blue flame of the propane gas torch for an initial period of one minute. This test specimen should be contained in a suitable steel frame to prevent the spread of flame igniting the sample's edges. During this time, observations of the heat effects on the specimen should be recorded.

#### 4.2 Acceptance criteria

At the end of the one minute period, the burner should be removed and the area of flame impingement should not support combustion more than 30 s after being removed from the burner.

#### 4.3 Additional information

After completing the test specified in paragraph 4.1, the specimen should then be immediately re-exposed, on the impingement point, by the heat source to establish the total burn-through time of the respective lay-up. Total burn-through time is taken as flaming to appear on the unexposed surface.

### **Test report**

5.1 The fire-retardant test report should include the following information:

- .1 name of testing body;
- .2 name of manufacturer of the material;
- .3 date of supply of the materials and of tests;
- .4 name or identification of the material;
- .5 description of the material;
- .6 density of the material;
- .7 description of the specimens;
- .8 test method;
- .9 test results including all observations; and
- .10 designation of the material according to the test criteria specified in paragraph 3.5.

5.2 The flame-resistant test report should include the following information:

- .1 name of testing body;
- .2 boat manufacturer;
- .3 date of material test;
- .4 boat type;

- .5 description of the specimen;
  - .6 time for flame extinguishments;
  - .7 burn-through time; and
  - .8 designation of the material according to the test criteria specified in paragraph 4.2.
-